**Amendments to the Claims:** 

This listing of claims will replace all prior versions, and listings of claims in the

application:

**Listing of Claims:** 

Please amend the claims as shown.

Claims 1-33. (Cancelled).

Claim 34. (Currently Amended) A process for preparing a shell-type catalyst comprising:

a) applying a suspension to a substantially nonporous inorganic support material having a BET

surface area of less than 80 m<sup>2</sup>/g [[a]] the suspension consisting essentially of:

(i) at least one water soluble catalytically active metal compound; and

(ii) a substantially water insoluble coating compound selected from the group consisting of:

SiO2; Al2O3, TiO2 and ZrO2; SiO2, Al2O3, TiO2 and ZrO2;

b) drying said suspension onto said support material; and

c) activating the preparation of step b) in a reducing gas stream.

Claim 35. (Currently Amended) The process [[of]] according to claim 34, wherein said

suspension consists of said water soluble metal compound and said substantially water insoluble

coating compound selected from the group consisting of: SiO<sub>2</sub>; Al<sub>2</sub>O<sub>3</sub>. TiO<sub>2</sub> and ZrO<sub>2</sub>. SiO<sub>2</sub>,

Al<sub>2</sub>O<sub>3</sub> TiO<sub>2</sub> and ZrO<sub>2</sub>

Claim 36. (Currently Amended) The process of either according to claim 34 or 35, wherein

said support material comprises a granulate or molded article of at least one member selected

from the group consisting of: glass; quartz; ceramic; silica; alumina; graphite; molded carbon;

Page 2 of 8

LIT/875273.1

metal; or steatite glass, quartz, ceramic, silica, alumina, graphite, molded carbon, metal and steatite.

Claim 37. (Currently Amended) The process of either according to claim 34 or 35, wherein said support material comprises a molded article of at least one member selected from the group consisting of SiO<sub>2</sub> and Al<sub>2</sub>O<sub>3</sub>.

Claim 38. (Currently Amended) The process [[of]] <u>according to claim 36</u>, wherein said molded article comprises at least one member selected from the group consisting of: a hollow extrudate; solid extrudate; sphere; granule; tablet; and strand a hollow extrudate, solid extrudate, sphere, granule, tablet and strand.

Claim 39. (Currently Amended) The process of either according to claim 34 or 35, wherein said support material has a diameter from 0.5 mm to 50 mm.

Claim 40. (Currently Amended) The process of either according to claim 34 or 35, wherein the BET surface of said support material is less than 10 m<sup>2</sup>/g.

Claim 41. (Currently Amended) The process of either according to claim 34 or 35, wherein said substantially nonporous support material has a pore volume of less than 0.5 ml/g.

Claim 42. (Currently Amended) The process of either according to claim 34 or 35, wherein said substantially nonporous support material has a pore volume of less than 0.1 ml/g.

Claim 43. (Currently Amended) The process of either according to claim 34 or 35, wherein said support material has an Fe<sub>2</sub>O<sub>3</sub> content of less than 0.5% wt.

Claim 44. (Currently Amended) The process of either according to claim 34 or 35, wherein said water soluble catalytically active metal compound is a water soluble noble metal compound

selected from the group consisting of: Ru; Rh; Pd; Ag; Os; Ir; Pt; and Au. Ru, Rh, Pd, Ag, Os, Ir, Pt and Au.

Claim 45. (Currently Amended) The process [[of]] according to claim 44, wherein said water soluble metal compound is in the form of an oxide, hydroxide, carbonate, halide, nitrate, salt of an organic acid or a complex.

Claim 46. (Currently Amended) The process [[of]] according to claim 44, wherein said suspension contains greater than 1% wt. aqueous solution of said water soluble noble metal compound calculated as the metal.

Claim 47. (Currently Amended) The process of either according to claim 44, wherein said suspension contains >5% wt. aqueous solution of said water soluble noble metal compound, calculated as the metal.

Claim 48. (Currently Amended) The process of either according to claim 44, wherein at least 0.01% wt. of said noble metal compound, calculated as the metal, is soluble in water at 30°C.

Claim 49. (Currently Amended) The process of either according to claim 34 or 35, wherein the maximum average agglomerate size of said oxide is 15 µm.

Claim 50. (Currently Amended) The process of either according to claim 34 or 35, wherein the agglomerate size of said oxide is 3  $\mu$ m to 7  $\mu$ m.

Claim 51. (Currently Amended) The process of either according to claim 34 or 35, wherein the BET surface area of said water insoluble coating compound is from 50 m<sup>2</sup>/g to 500 m<sup>2</sup>/g.

Claim 52. (Currently Amended) The process of either according to claim 34 or 35, wherein the compacted density of said insoluble coating compound is from 10 g/l to 800 g/l.

calculated as the metal is from 0.1:1 to 5:1.

- Claim 53. (Currently Amended) The process of either according to claim 34 or 35, wherein the weight ratio of said water soluble noble metal compound to said insoluble coating compound
- Claim 54. (Currently Amended) The process [[of]] according to claim 53, wherein the weight ratio of said noble metal compound to said insoluble coating compound is between 0.5:1 and 2:1.
- Claim 55. (Currently Amended) The process of either according to claim 34 or 35, wherein the weight ratio of said noble metal compound, calculated as the metal, to the total weight of the shell-type catalyst is between 0.0001:1 and 0.02:1.
- Claim 56. (Currently Amended) The process of either according to claim 34 or 35, wherein the weight ratio of the coating compound to the total weight of the shell-type catalyst, calculated as the metal, is between 0.005:1 and 0.04:1.
- Claim 57. (Currently Amended) The process of either according to claim 34 or 35, wherein the thickness of the coating shell of the catalyst is from 0.1 µm to 20 µm.
- Claim 58. (Currently Amended) The process of either according to claim 34 or 35, wherein the concentration of the water soluble metal component, calculated as the metal, is from 0.1% wt. to 1% wt. based on the catalyst.
- Claim 59. (Currently Amended) The process of either according to claim 34 or 35, wherein the concentration of the water insoluble coating material, calculated as the metal, is from 0.05% wt. to 1% wt. based on the catalyst.
- Claim 60. (Currently Amended) The process of either according to claim 34 or 35, wherein said reducing gas stream contains hydrogen.
- Claim 61. (New) The shell catalyst produced by the process according to claim 34.